

Camelot Tor IAR # 32239

Register no: JW0806

Sire: Jolimont Attitude (solid white)

Dam: Camelot Ivoire (solid white)


44 months old white male Huacaya alpaca

| DENSITY: | | LENGTH: 339 days wool growth | |
|--|------|-------------------------------------|------|
| Mean fibre diameter (microns) | 24.2 | Crimps per cm | 2.7 |
| Secondary follicle to primary follicle ratio | 9.6 | Fibre growth rate (mm per day) | 0.31 |
| Follicle density (per mm ²) | 57.0 | Fibre length to staple length ratio | 1.05 |
| SKIN THICKNESS (mm compressed): | 2.79 | CYLINDRICAL FIBRES (%): | |

FIBRE LENGTH DISTRIBUTION

FIBRE LENGTH

| | |
|------------------|--------------|
| Mean (mm) | 108.1 |
| SD (mm) | 31.4 |
| CV (%) | 29.0 |
| Min (mm) | 30.0 |
| Max (mm) | 155.0 |



Skin and fleece tests conducted by Dr. J.E. Watts M.V.Sc., Ph.D.

5 November 2006